



## TEST REPORT

Report nr.: **1604964-001**  
Report date: **22-set-16**  
Acceptance code: **1604964**  
Acceptance date: **15-set-16**  
Start test date: **15-set-16**  
End test date: **22-set-16**  
References: **---**

Customer code: 5485

**To:**  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:  
sig. Sergio Sala Crist  
Tel.nr: +39 031 879632  
Fax.nr.: +39 031 855397

Article description: **TIZIANO**  
Declared composition: **100% Trevira**  
End use: **Furnishing**  
Typology: **Fabric**  
Return: **Specimens enclosed**  
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.  
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
<b>14063 RESISTANCE TO ABRASION (Martindale) - DETERMINATION OF SPECIMEN BREAKDOWN</b>		
<b>Method:</b>	UNI EN ISO 12947-2:2000 + EC 1-2010	
<b>Instrument:</b>	Abrasion Tester Martindale J.Heal - 103	
SPECIMEN BREAKDOWN		
Specimen breakdown is reached when:		
- in woven fabric, when two separate threads are completely broken;		
- in knitted fabric, when one thread is broken causing a hole;		
- in pile fabric, when the pile is fully worn off;		
- in nonwoven fabric, when the first hole is of a diameter at least equal to 0,5 mm.		
Date of test:		16/09/16
Pretreatment carried out		no one
First specimen: cycles to end point	cycles	43000
Second specimen: cycles to end point	cycles	43000
Third specimen: cycles to end point	cycles	48000
Average	cycles	44667
Confidence limits		-
Load applied	kPa	12
Change in colour at the end point (when stated)	grade	4
Pilling occurred	cycles	-
Deviation from procedure		-
Enclosed:	nr.	1



Report nr.

**1604964-001**

-----  
**END OF TEST REPORT**  
-----

**Supervisor Head**

p.i. Giovanna Baglio

**Technical Head**

dott. Marco Piu