

## TEST REPORT

Report nr.: **2000396-001**

Report date: **05-feb-20**

Acceptance code: **2000396**

Acceptance date: **21-gen-20**

Start test date: **21-gen-20**

End test date: **05-feb-20**

References: ---

Customer code: 5485

**To:**  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

**ZELDA**

**63% Cotton - 29% Viscose - 8% Polyester**

**Furnishing**

**Fabric**

**No requested**

The results reported herein refer exclusively to the tested sample as received and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory. The informations as Article Description, Declared Composition and Tipology listed above are data supplied by the Customer for which this Laboratory declines any responsibility.

TEST	M.U.	RESULTS
<b>1443 SLIPPAGE RESISTANCE OF YARNS AT A SEAM - fixed load</b>		
<b>Method:</b>	UNI EN ISO 13936-2/2004	
<b>Instrument:</b>	CRE Dynamometer	
<b>FURNISHING:</b>		
Sewing thread : 100% polyester, Linear density 74 tex		
Plain lockstitch type n.301 (ISO 4915:1991)		
Needle: number metric 110		
Stitches/100 mm: 32 ± 2		
Date of test:		28/01/2020
Force applied	N	180
WARP over WEFT - seam opening	mm	3,0
WEFT over WARP - seam opening	mm	3,0
Number of specimens for each direction	n.	5
Statement occurred:		-

(\*) = the tests marked with asterisk are not accredited by Accredia.

Report nr.

**2000396-001**

TEST

M.U.

RESULTS

----- **END OF TEST REPORT** -----

**Technical Head**

Enrica Baldini

