

## TEST REPORT

Report nr.: **2000396-005**

Report date: **05-feb-20**

Acceptance code: **2000396**

Acceptance date: **21-gen-20**

Start test date: **21-gen-20**

End test date: **05-feb-20**

References: ---

Customer code: 5485

**To:**  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

**ZELDA**

**63% Cotton - 29% Viscose - 8% Polyester**

**Furnishing**

**Fabric**

**Specimens enclosed**

The results reported herein refer exclusively to the tested sample as received and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory. The informations as Article Description, Declared Composition and Tipology listed above are data supplied by the Customer for which this Laboratory declines any responsibility.

TEST	M.U.	RESULTS
<b>14323-ar PROPENSITY TO SURFACE PILLING</b>		
<b>(Martindale)</b>		
<b>Method:</b>	UNI EN ISO 12945-2/02	
<b>Instrument:</b>	Abrasion Tester Martindale	
Number of observers: 02		
EXPLANATORY NOTE OF THE RESULTS		
Grade 5: no change		
Grade 4: slight surface fuzzing and/or partially formed pills.		
Grade 3: moderate surface fuzzing and/or moderate pilling. Pills of varying size and density partially covering the specimen surface.		
Grade 2: distinct surface fuzzing and/or distinct pilling. Pills of varying size and density covering a large proportion of the specimens surface.		
Grade 1: dense surface fuzzing and/or severe pilling. Pills of varying size and density covering the whole of the specimen surface.		
Date of test:		24-01-2020
Pretreatment carried out		No one
Change at 500 revs.	grade	5
Change at 1000 revs.	grade	4-5
Change at 2000 revs.	grade	4
Change at 5000 revs.	grade	3-4
The final grade above refers to pilling and fuzzing.		
Number of specimens:	nr.	3

(\*) = the tests marked with asterisk are not accredited by Accredia.

Report nr.

**2000396-005**

TEST	M.U.	RESULTS
Abradent:		Abradant wool
Load applied:	g	415
Deviation from procedure		.

-----  
**END OF TEST REPORT**  
-----

**Technical Head**

Enrica Baldini

