



## TEST REPORT

Report nr.: **1607146-001**  
Report date: **03-gen-17**  
Acceptance code: **1607146**  
Acceptance date: **22-dic-16**  
Start test date: **22-dic-16**  
End test date: **03-gen-17**  
References: **---**

Customer code: 5485

**To:**  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:  
sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Article description: **SUPERNOVA**  
Declared composition: **100% Trevira**  
End use: **Furnishing**  
Typology: **Fabric**  
Return: **Specimens enclosed**  
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.  
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
<b>14323-ar PROPENSITY TO SURFACE PILLING</b>		
<b>(Martindale)</b>		
<b>Method:</b> UNI EN ISO 12945-2/02		
<b>Instrument:</b> Abrasion Tester Martindale J.Heal - NU - 406		
Number of observers: 02		
<b>EXPLANATORY NOTE OF THE RESULTS</b>		
Grade 5: no change		
Grade 4: slight surface fuzzing and/or partially formed pills.		
Grade 3: moderate surface fuzzing and/or moderate pilling. Pills of varying size and density partially covering the specimen surface.		
Grade 2: distinct surface fuzzing and/or distinct pilling. Pills of varying size and density covering a large proportion of the specimens surface.		
Grade 1: dense surface fuzzing and/or severe pilling. Pills of varying size and density covering the whole of the specimen surface.		
Date of test:		02/01/2017
Pretreatment carried out		no one
Change at 500 revs.	grade	5
Change at 1000 revs.	grade	5
Change at 2000 revs.	grade	5
Change at 5000 revs.	grade	5
Number of specimens:	nr.	3
Abradent:		wool
Load applied:	g	415
Deviation from procedure		-



Report nr.

**1607146-001**

-----  
**END OF TEST REPORT**  
-----

**Supervisor Head**

p.i. Giovanna Baglio

**Technical Head**

dott. Marco Piu