



LAB n° 0045

TEST REPORT

Report nr.: **1701278-001**Report date: **10-mar-17**Acceptance code: **1701278**Acceptance date: **06-mar-17**Start test date: **06-mar-17**End test date: **10-mar-17**References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr. +39 031 855397

Sampling by customer

Article description:

SUPERNOVA

Declared composition:

100% Trevira

End use:

Furnishing

Typology:

Fabric

Return:

No requested

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
14443 SLIPPAGE RESISTANCE OF YARNS AT A SEAM - fixed load		-
Method: UNI EN ISO 13936-2/2004		
Instrument: CRE Dynamometer		
FURNISHING: Sewing thread : 100% polyester, Linear density 74 tex Plain lockstitch type n.301 (ISO 4915:1991) Needle: number metric 110 Stitches/100 mm: 32 ± 2		
Date of test:		10/03/2017
Force applied	N	180
WARP over WEFT - seam opening	mm	3,0
WEFT over WARP - seam opening	mm	4,3
Number of specimens for each direction	n.	5
Statement occurred:		-

(*) = the tests marked with asterisk are not accredited by Accredia.



Report nr.

1701278-001



LAB n° 0045

END OF TEST REPORT

Technical Head

Enrica Baldini