



TEST REPORT

Report nr.: **1607149-001**
Report date: **03-gen-17**
Acceptance code: **1607149**
Acceptance date: **22-dic-16**
Start test date: **22-dic-16**
End test date: **03-gen-17**
References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Article description: **SUPERNOVA**
Declared composition: **100% Trevira**
End use: **Furnishing**
Typology: **Fabric**
Return: **Specimens enclosed**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
14203 TENSILE STRENGTH - MAXIMUM FORCE AND ELONGATION AT MAXIMUM FORCE USING THE STRIP METHOD		
Method:	UNI EN ISO 13934-1:2013	
Instrument:	CRE Dynamometer	
Date of test:		02/01/2017
Gauge length	mm	200
Elongation speed used	mm/min	100
Pretension applied	N	10
Specimens condition		Conditioned
Number of specimens for each direction	n.	5
WARP - maximum force - average	N	1678
WARP - elongation to max. force - average	%	31,0
WEFT - maximum force - average	N	840
WEFT - elongation to max. force - average	%	30,0
Number of specimens rejected:	nr.	0
Deviation from procedure		-



Report nr.

1607149-001

END OF TEST REPORT

Supervisor Head

p.i. Giovanna Baglio

Technical Head

dott. Marco Piu