



## REPORT

Report nr.: **1600359-001**  
Report date: **29-gen-16**  
Acceptance code: **1600359**  
Acceptance date: **21-gen-16**  
Start test date: **21-gen-16**  
End test date: **29-gen-16**  
References: **---**

Customer code: 5485

**To:**  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:  
sig. Sergio Sala Crist

Tel.nr: +39 031 879632  
Fax.nr.: +39 031 855397

Article description: **TUNDRA 01**  
Declared composition: **42% Viscose - 36% Cotton - 16% Acrylic - 6% Polyester**  
End use: **Furnishing**  
Typology: **Fabric**  
Return: **No requested**  
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.  
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
<b>14203 TENSILE STRENGTH - strip method</b>		
<b>Method:</b>	UNI EN ISO 13934-1:2013	
<b>Instrument:</b>	CRE Dynamometer	
Date of test:		28/01/2016
Gauge length	mm	200
Elongation speed used	mm/min	100
Pretension applied	N	10
Specimens condition		Conditioned
WARP - maximum force - average	N	1310
WARP - elongation to max. force - average	%	23,0
WEFT - maximum force - average	N	1255
WEFT - elongation to max. force - average	%	24,0
Number of specimens rejected:	nr.	0
Deviation from procedure		-



Report nr.

**1600359-001**

-----  
**END OF REPORT**  
-----

**Supervisor Head**

p.i. Giovanna Baglio

**Technical Head**

dott. Marco Piu