



REPORT

Report nr.: **1600476-001**

Report date: **29-gen-16**

Acceptance code: **1600476**

Acceptance date: **22-gen-16**

Start test date: **22-gen-16**

End test date: **29-gen-16**

References: **---**

Customer code: **5485**

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist

Tel.nr: **+39 031 879632**

Fax.nr.: **+39 031 855397**

Article description: **VOYAGER**
Declared composition: **100% Trevira**
End use: **Furnishing**
Typology: **Fabric**
Return: **No requested**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
14203 TENSILE STRENGTH - strip method		
Method:	UNI EN ISO 13934-1:2013	
Instrument:	CRE Dynamometer	
Date of test:		28/01/2016
Gauge length	mm	200
Elongation speed used	mm/min	100
Pretension applied	N	5
Specimens condition		Conditioned
WARP - maximum force - average	N	990
WARP - elongation to max. force - average	%	35,5
WEFT - maximum force - average	N	753
WEFT - elongation to max. force - average	%	29,0
Number of specimens rejected:	nr.	0
Deviation from procedure		-

Centro Tessile Serico



Centro Tessile Serico Spa consortile
via Castelnuovo, 3 22100 Como, Italia
P.IVA - C.F. 02381270137
Capitale sociale 193.807,38 i.v.
mailbox@textilecomo.com
www.textilecomo.com

Servizio Clienti Laboratorio +39 031 3312120
Segreteria Laboratorio +39 031 3312121-170-171
Segreteria di Direzione
e Amministrazione +39 031 3312102
Contabilità +39 031 3312154
Area Certificazione +39 031 3312134
Marchio Serico +39 031 3312132
Fax +39 031 3312180

Report nr.

1600476-001

END OF REPORT

Supervisor Head

p.i. Giovanna Baglio

Technical Head

dott. Marco Piu