



REPORT

Report nr.: **1600477-001**
Report date: **26-gen-16**
Acceptance code: **1600477**
Acceptance date: **22-gen-16**
Start test date: **22-gen-16**
End test date: **26-gen-16**
References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist

Tel.nr: +39 031 879632
Fax.nr.: +39 031 855397

Article description: **VOYAGER**
Declared composition: **100% Trevira**
End use: **Furnishing**
Typology: **Fabric**
Return: **Specimens enclosed**
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
------	------	---------

14323-ar PROPENSITY TO SURFACE PILLING
(Martindale)

Method: UNI EN ISO 12945-2/02
Instrument: Abrasion Tester Martindale J.Heal - NU - 406
Number of observers: 02

EXPLANATORY NOTE OF THE RESULTS

Grade 5: no change
Grade 4: slight surface fuzzing and/or partially formed pills.
Grade 3: moderate surface fuzzing and/or moderate pilling. Pills of varying size and density partially covering the specimen surface.
Grade 2: distinct surface fuzzing and/or distinct pilling. Pills of varying size and density covering a large proportion of the specimens surface.
Grade 1: dense surface fuzzing and/or severe pilling. Pills of varying size and density covering the whole of the specimen surface.

Date of test: 25-01-2016

Pretreatment carried out NO ONE

Change at 500 revs.	grade	4-5
---------------------	-------	-----

Change at 1000 revs.	grade	4-5
----------------------	-------	-----

Change at 2000 revs.	grade	4-5
----------------------	-------	-----

Change at 5000 revs.	grade	4
----------------------	-------	---

The final grade above refers to pilling and fuzzing.

Number of specimens:	nr.	3
----------------------	-----	---

Abradent:		Abradant wool
-----------	--	---------------

Load applied:	g	415
---------------	---	-----

Centro Tessile Serico



Centro Tessile Serico Spa consortile
via Castelnuovo, 3 22100 Como, Italia
P.IVA - C.F. 02381270137
Capitale sociale 193.807,38 i.v.
mailbox@textilecomo.com
www.textilecomo.com

Servizio Clienti Laboratorio +39 031 3312120
Segreteria Laboratorio +39 031 3312121-170-171
Segreteria di Direzione
e Amministrazione +39 031 3312102
Contabilità +39 031 3312154
Area Certificazione +39 031 3312134
Marchio Serico +39 031 3312132
Fax +39 031 3312180

Report nr.

1600477-001

Deviation from procedure

END OF REPORT

Supervisor Head

p.i. Giovanna Baglio

Technical Head

dott. Marco Piu