



## REPORT

Report nr.: **1600479-001**  
Report date: **27-gen-16**  
Acceptance code: **1600479**  
Acceptance date: **22-gen-16**  
Start test date: **22-gen-16**  
End test date: **27-gen-16**  
References: **---**

Customer code: 5485

To:  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:  
sig. Sergio Sala Crist

Tel.nr: +39 031 879632  
Fax.nr.: +39 031 855397

Article description: **VOYAGER**  
Declared composition: **100% Trevira**  
End use: **Furnishing**  
Typology: **Fabric**  
Return: **Specimens enclosed**  
Sampling by customer

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.  
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
------	------	---------

**25135 DIMENSIONAL CHANGES TO DOMESTIC  
WASHING AND DRYING**

Method: UNI EN ISO 3759:2011; UNI EN ISO 6330:2012;  
UNI EN ISO 5077:2008  
Instrument: WASHING-MACHINE ELECTROLUX WASCATOR  
mod. FOM 71 MP LAB

Programme of washing: 4N - normal agitation  
Test Temperature: 40°C  
Drying procedure: type C - Flat dry  
Detergent used: ECE (ref.A) - Sodium Perborated - TAED  
Total air-dry- mass (specimens and ballast): 2,0 kg  
Type of ballast used: Type III (polyester)

DIMENSIONAL CHANGE - WIDTH direction	%	0,0
DIMENSIONAL CHANGE - LENGHT direction	%	-1,0

### END OF REPORT

Supervisor Head

p.i. Giovanna Baglio

Technical Head

dott. Marco Piu