

## TEST REPORT

Report nr.: **2000403-002**

Report date: **19-feb-20**

Acceptance code: **2000403**

Acceptance date: **22-gen-20**

Start test date: **22-gen-20**

End test date: **19-feb-20**

References: ---

Customer code: 5485

**To:**  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

**MAGNIFICO**  
**100% Polyester**  
**Furnishing**  
**Fabric**  
**No requested**

The results reported herein refer exclusively to the tested sample as received and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory. The informations as Article Description, Declared Composition and Tipology listed above are data supplied by the Customer for which this Laboratory declines any responsibility.

TEST	M.U.	RESULTS
<b>14253 TEAR PROPERTIES OF FABRICS WING SHAPED (2 directions)</b>		
<b>Method:</b>	UNI EN ISO 13937-3/02	
<b>Instrument:</b>	CRE Dynamometer	
Date of test:		30/01/2020
Tear force of yarns WARP - Average	N	71
Tear force of yarns WEFT - Average	N	72
Number of specimens for each direction	n.	5
Number of specimens rejected:	nr.	0
Deviation from procedure		-

(\*) = the tests marked with asterisk are not accredited by Accredia.

Report nr.

**2000403-002**

TEST

M.U.

RESULTS

----- **END OF TEST REPORT** -----

**Technical Head**

Enrica Baldini

