

Test Report No.:	2207468-001	
Date Test Report	02-nov-22	Customer Code 05485
Acceptance:	2207468	Dear:
Arrival date sample	26-ott-22	MARIO SIRTORI SPA
Start date test	26-ott-22	via Papa Giovanni XXIII 10
End date test	02-nov-22	23845 COSTA MASNAGA (LC) Italia
References:		C.a. sig. Sergio Sala Crist
		Phone: +39 031 879632
Sampling Mode:	Sampling by Customer *	
[C] Item: GIADA [C] Declared Composition: 60% PC - 19% CO - 11% VI - 6% PL - 4% AF [C] End use: furnishing [C] Typology: fabric Return: no requested		

Test Results

Test	Method	U.M.	Result
15076 UPHOLSTERY FURNITURE:	BS 5852-1:1979		.
ASSESSMENT OF THE IGNITABILITY BY MATCH FLAME			
Start date test	28/10/2022		
End date test	02/11/2022		
Instrument: Small Test Rig and burner			
Test carried out on			COVER FABRIC
Pretreatment carried out			none
Ignition source			source 1 (MATCH FLAME EQUIVALENT)
Materials of test assembly			.
Upholstery filling: NON fire retardant polyurethane foam with a density of 21 kg/m³			
Inner cover: -			
Outer cover: SEE ARTICLE DESCRIPTION			
TEST RESULT			SAMPLE PASSES THE TEST
Deviations from the method			none
Annex n.			1F
Details of the test results related to each specimen can be seen in the annex of this test report.			

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2207468-001**

Test	Method	U.M.	Result
------	--------	------	--------

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
Via Castelnuovo, 3 – 22100 Como Italia
Tel. +39 031331211 Fax +39 0313312149
Amministrazione/Contabilità +39 0313312102-154
P.IVA – C.F. 03900470133
Capitale sociale euro 600.000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Annex n. 1F to test report n. 2207468-001

DETAILS OF TEST RESULTS

Test executed according to BS 5852-Part1:1979

Fire test for furniture - Methods of test for the ignitability by smokers' materials of upholstered composites for seating - Ignition source 1: BUTANE FLAME

Ref. Schedule 5, Part 1 'The Match Test' of Furniture and Furnishing (Fire) (Safety) Regulations 1988 S.I. 1324

Sample description: **GIADA**

Declared composition: **60% PC - 19% CO - 11% VI - 6% PL - 4% AF**

Conditioning of test specimen: **16 hours at 20 ± 5 °C, 50 ± 20 % r.h.**

Testing temperature and r.h.: **17°C, 69% r.h.**

Filling specification: **non fire-retardant polyurethane foam with a density of 21 kg/m³**

Sample pre-treatment: **sample wasn't subjected to any pretreatment**

Date of test: **02.11.2022**

Specimen number	1	2
Time of flaming from removal of the source (s)	0	4
Time of progressive smouldering from removal of the source (s)	17	23
Sample melting (YES/NO)	YES	YES
Sample dripping (YES/NO)	NO	NO
Sample charring (YES/NO)	YES	YES
Progressive smouldering observed after the final examination (YES/NO)	NO	NO
MATCH TEST RESULT (PASS/FAIL)	PASS	PASS

The following test result relate only to the ignitability of the combination of materials under the particular conditions of test. They are not intended as a means of assessing the full potential fire hazard of the material in use.

The probability that the criteria represent the truth observation is equal to 95%.

The Laboratory Manager
Eusto Albionio