



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com
www.textilecomo.com



LAB N° 0045 L

Test Report No.:	2007899-001	
Date Test Report	08-gen-21	Customer Code 05485
Acceptance:	2007899	Dear:
Arrival date sample	17-dic-20	MARIO SIRTORI SPA
Start date test	17-dic-20	via Papa Giovanni XXIII 10
End date test	08-gen-21	23845 COSTA MASNAGA (LC) Italia
References:		C.a. sig. Sergio Sala Crist
		Phone: +39 031 879632
Sampling Mode:	Sampling by Customer *	
[C] Item:	GIADA	
[C] Declared Composition:	60% Acrylic - 19% Cotton - 11% Viscose - 6% Polyester - 4% Other fibers	
[C] End use:	Furnishing	
[C] Typology:	Fabric	
Return:	Specimens enclosed	

Test Results

Test	Method	U.M.	Result
14063-ABRASION RESISTANCE (Martindale method): SPECIMENS BREAKDOWN	UNI EN ISO 12947-2:2017		.
Instrument: Abrasion Tester Martindale			
SPECIMEN BREAKDOWN (END POINT): The breakdown point of the specimen is reached when: - Woven fabric (without pile): Two threads completely broken; - Knitted fabric (without pile): One thread completely broken; - Cut pile woven fabric: Two threads completely broken or fully worn of area; - Cut pile knitted fabric: One thread completely broken or fully worn of area; - Woven pile fabric with chenille yarns: Two threads completely broken or fully worn of area; - Knitted pile fabric with chenille yarns: One thread completely broken or fully worn of area; - Woven uncut pile fabric: Two threads completely broken or fully worn of area; - Knitted uncut pile fabric: One thread completely broken or fully worn of area; - Woven raised fabric: Two threads completely broken; - Knitted raised fabric: One thread completely broken; - Flocked fabrics: tested area completely worn off; - Non-woven fabrics: surface layer shows a worn of diameter 2,5 mm			
Date of test			22/12/2020
Pretreatment carried out			No one
First specimen: cycles to end point		cycles	90000
Second specimen: cycles to end point		cycles	90000
Third specimen: cycles to end point		cycles	90000
QUOTED RESULT: the lowest individual value		cycles	90000
Load applied		kpa	12
Change in appearance			Total chenille pile loss at 70000

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.



Centro Tessile Serico Sostenibile Srl
via Castelnuovo, 3 - 22100 Como Italia
Pho +39 031 3312111/120 Fax: +39 0313312149
Amministrazione/Contabilità +39 031 3312102-154
P. IVA - C.F. 003900470133
Capitale sociale euro 600000,00 iv
mailbox@textilecomo.com



LAB N° 0045 L

Test Report No.: **2007899-001**

Test	Method	U.M.	Result
Deviation from procedure			.
n. attachments		No.	1

The Laboratory Manager

Fausto Albonico

END OF REPORT

(*) = The tests marked in this way are not accredited by Accredia

The Results contained in this Report refer only to the Sample as received and do not imply an approval of the tested product by the Laboratory of the Centro Tessile Serico Sostenibile Srl. Unless otherwise specified, the side examined / straight of use is indicated by the Customer: this information can influence the results of the tests and therefore the Test Laboratory declines all responsibility.

This Report may not be reproduced in part, unless written permission of Centro Tessile Serico Sostenibile Srl Laboratory.

[C] = Information provided by the Customer, of which the Centro Tessile Serico Sostenibile Srl Laboratory declines all responsibility.