



LAB n° 0045

## TEST REPORT

Report nr.: **1702423-005**

Report date: **11-mag-17**

Acceptance code: **1702423**

Acceptance date: **04-mag-17**

Start test date: **04-mag-17**

End test date: **11-mag-17**

References: **---**

Customer code: 5485

**To:**  
**MARIO SIRTORI SPA**  
**via Papa Giovanni XXIII 10**  
**23845 COSTA MASNAGA (LC)**  
**Italia**

To the attention of:  
sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr. +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

**PLUTONE**  
**100% TREVIRA**  
**Furnishing**  
**Fabric**  
**No requested**

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.  
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
<b>14203 TENSILE STRENGTH - MAXIMUM FORCE AND ELONGATION AT MAXIMUM FORCE USING THE STRIP METHOD</b>		
<b>Method:</b>	UNI EN ISO 13934-1:2013	
<b>Instrument:</b>	CRE Dynamometer	
Date of test:		08/05/17
Gauge length	mm	200
Elongation speed used	mm/min	100
Pretension applied	N	5
Specimens condition		Original
Number of specimens for each direction	n.	5
WARP - maximum force - average	N	1622
WARP - elongation to max. force - average	%	31,0
WEFT - maximum force - average	N	1189
WEFT - elongation to max. force - average	%	36,0
Number of specimens rejected:	nr.	0
Deviation from procedure		-

(\*) = the tests marked with asterisk are not accredited by Accredia.



Report nr.

**1702423-005**



LAB n° 0045

-----  
**END OF TEST REPORT**  
-----

**Technical Head**

Enrica Baldini