



LAB n° 0045

TEST REPORT

Report nr.: **1702423-006**

Report date: **11-mag-17**

Acceptance code: **1702423**

Acceptance date: **04-mag-17**

Start test date: **04-mag-17**

End test date: **11-mag-17**

References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr. +39 031 855397

Sampling by customer

Article description:

Declared composition:

End use:

Typology:

Return:

PLUTONE

100% TREVIRA

Furnishing

Fabric

Specimens enclosed

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
25135 DIMENSIONAL CHANGES TO DOMESTIC WASHING AND DRYING		
Method:	UNI EN ISO 3759:2011; UNI EN ISO 6330:2012; UNI EN ISO 5077:2008	
Instrument:	WASHING-MACHINE ELECTROLUX WASCATOR mod. FOM 71 MP LAB	
Programme of washing: 3N - normal agitation		
Test Temperature: 30°C		
Drying procedure: type C - Flat dry		
Detergent used: ECE (ref.A) - Sodium Perborated - TAED		
Total air-dry- mass (specimens and ballast): 2,0 kg		
Type of ballast used: Type III (polyester)		
DIMENSIONAL CHANGE - WIDTH direction	%	-1,6
DIMENSIONAL CHANGE - LENGHT direction	%	-1,1

(*) = the tests marked with asterisk are not accredited by Accredia.



Report nr.

1702423-006



LAB n° 0045

END OF TEST REPORT

Technical Head

Enrica Baldini