



LAB n° 0045

TEST REPORT

Report nr.: **1702423-003**Report date: **11-mag-17**Acceptance code: **1702423**Acceptance date: **04-mag-17**Start test date: **04-mag-17**End test date: **11-mag-17**References: **---**

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:
sig. Sergio Sala Crist

Tel.nr: +39 031 879632

Fax.nr. +39 031 855397

Sampling by customer

Article description:

PLUTONE

Declared composition:

100% TREVIRA

End use:

Furnishing

Typology:

Fabric

Return:

No requested

The results reported herein refer to the tested samples only and do not involve any product approval by Centro Tessile Serico.
This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory.

TEST	M.U.	RESULTS
------	------	---------

14443 SLIPPAGE RESISTANCE OF YARNS AT A SEAM - fixed load		-
--	--	---

Method:	UNI EN ISO 13936-2/2004
----------------	-------------------------

Instrument:	CRE Dynamometer
--------------------	-----------------

FURNISHING:

Sewing thread : 100% polyester, Linear density 74 tex

Plain lockstitch type n.301 (ISO 4915:1991)

Needle: number metric 110

Stitches/100 mm: 32 ± 2

Date of test:

08/05/17

Force applied

N

180

WARP over WEFT - seam opening

mm

4,4

WEFT over WARP - seam opening

mm

2,6

Number of specimens for each direction

n.

5

Statement occurred:

-

(*) = the tests marked with asterisk are not accredited by Accredia.



Report nr.

1702423-003



LAB n° 0045

END OF TEST REPORT

Technical Head

Enrica Baldini