

TEST REPORT

Report nr.: **2000554-002**

Report date: **06-feb-20**

Acceptance code: **2000554**

Acceptance date: **28-gen-20**

Start test date: **28-gen-20**

End test date: **06-feb-20**

References: ---

Customer code: 5485

To:
MARIO SIRTORI SPA
via Papa Giovanni XXIII 10
23845 COSTA MASNAGA (LC)
Italia

To the attention of:

sig.ra Laura Misseri

Tel.nr: +39 031 879632

Fax.nr.: +39 031 855397

Sampling by customer

Article description:

Declared composition:

KATMANDU

36% Viscose - 32% Flax - 24% Acrylic - 4% Polyamide - 4% Polyester

End use:

Furnishing

Typology:

Fabric

Return:

No requested

The results reported herein refer exclusively to the tested sample as received and do not involve any product approval by Centro Tessile Serico. This document may not be reproduced other than in full, except with the prior written approval of the issuing Laboratory. The informations as Article Description, Declared Composition and Tipology listed above are data supplied by the Customer for which this Laboratory declines any responsibility.

TEST	M.U.	RESULTS
14253 TEAR PROPERTIES OF FABRICS WING SHAPED (2 directions)		
Method:	UNI EN ISO 13937-3/02	
Instrument:	CRE Dynamometer	
Date of test:		06/02/2020
Tear force of yarns WARP - Average	N	288
Tear force of yarns WEFT - Average	N	451
Number of specimens for each direction	n.	5
Number of specimens rejected:	nr.	0
Deviation from procedure		-

(*) = the tests marked with asterisk are not accredited by Accredia.

Report nr.

2000554-002

TEST

M.U.

RESULTS

----- **END OF TEST REPORT** -----

Technical Head

Enrica Baldini

